


PAROC Marine Slab 40



Certification Number VTT-C-11346-15-15 / Eurofins Expert Services Ltd, Kivimiehentie 4, FI-02150 Espoo, Finland

Short Description Stone wool slab. Also possible to use with facings AluCoat, G1, G2, G3, G4, G7, N3 and N5. See "Facings".

Application Thermal insulation on ships.

The notified body VTT Expert Services Ltd. (0809) performed and issued the certificates: Type-Examination (Module B) certificate No. VTT-C-11346-15-15

Nominal Density 40 kg/m³

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Dimensions

Dimensions	
Width x Length	Thickness
600 x 1200 mm	50 - 120 mm
In accordance with EN 822	In accordance with EN 823

Other Dimensions Other dimensions available on request.

Packaging

Package Type Plastic packs on pallet

Fire Properties


Other Fire Properties		
Property	Value	According to
Fire Classification (IMO)	Non-Combustible	IMO FTP 2010 Code Part 1

Thermal Conductivity (values announced by manufacturer)		
Property	Value	According to
Thermal Conductivity in 10 °C, λ_{10}	0,037 W/mK	EN 12667
Thermal Conductivity in 50 °C, λ_{50}	0,042 W/mK	EN 12667
Thermal Conductivity in 100 °C, λ_{100}	0,054 W/mK	EN 12667
Thermal Conductivity in 200 °C, λ_{200}	0,085 W/mK	EN 12667

Moisture Properties

Water Permeability		
Property	Value	According to
Water Absorption, Short Term WS, W_p	$\leq 1 \text{ kg/m}^2$	EN 1609


Facings



AluCoat




G1




G2



G3




G4



G7



N3



N5

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).