

Isogenopak® (Euroclass C_L-s3,d0)

Insulation Jacketing with permanent curl

Technical data

- ⇒ Permanent curl
- ⇒ Antistatic
- ⇒ Handy surface
- ⇒ Flexible
- ⇒ Will not splinter during riveting
- ⇒ High chemical resistance
- ⇒ No plasticizers
- ⇒ Physiologically safe in technical applications, including food processing operations
- ⇒ Non-aging and temperature-resistant from –20°C to +65°C
- ⇒ Light weight, approx. 500 g/m²
- ⇒ No CFCs or HCFCs used in the making of this product
- ⇒ Made using no silicone
- ⇒ Manufactured without the heavy metals cadmium, lead, chromium^{VI} or their compounds
- ⇒ No flammable drips in the event of a fire
- ⇒ Easy to work, for maximum installation productivity

Property	Value	Unit	Testing method
Tensile impact strength	≥ 300	kJ/m ²	DIN EN ISO 8256
Tensile strength	> 35	N/mm ²	DIN EN ISO 527
Modulus of elasticity	appr. 1800	N/mm ²	DIN EN ISO 527
Water vapour resistance μ	appr. 60000	-	DIN 52615
Linear heat expansion coefficient	1,5 x 10 ⁻⁴	1/K	Leitz-Dilatometer
Thermal conductivity	appr. 0.16	W/mK	at 20°C
Emissivity ε	97	%	ISO 10292 annex A
Film type	203/31		
Material	Rigid PVC		
Colour	Isogenopak®-grey (close to RAL 7035/7047) 75/7900-281		
Isogenopak® meets the requirements of DIN EN 15701			

Reaction to fire classification

C_L-s3, d0 acc. EN 13501-1:2007 + A1:2009

- Technical Approval SC0073-15
- Jacketing on Euroclass A1_L or A2_L –s2,d0 mineral wool products
- Fixing with plastic push in rivets or solution welding compound

Supply dimension

Thickness: 0,35 mm	Width: 1.400 mm	Length: 25 m
--------------------	-----------------	--------------

Installation notes

- Attach with plastic rivets spaced approx. 20 cm apart or solvent-based adhesive.
- Isogenopak® is not recommended for outdoor use (UV exposure).

Customs tariff number: 39 20 49 10

Klöckner Pentaplast Europe GmbH & Co. KG, Werk Gendorf, D-84504 Burgkirchen
Tel. +49 (0) 8679 / 7 5510 Fax +49 (0) 8679 / 7 5096 www.kpfilms.com

The information presented here is current as of the printing date. Please ask for the latest version of this brochure, if available. No warranty is expressed or implied herein with respect to specific product properties or fitness of the products for a particular use. Industrial property rights are to be observed.

We warrant a quality free of defects within the context of the General Terms of Sale of Klöckner Pentaplast Europe GmbH & Co. KG 03/2015 KW/SJ